

Delft University of Technology

Highly Water-Permeable Metal-Organic Framework MOF-303 Membranes for Desalination

Cong, Shenzhen; Yuan, Ye; Wang, Jixiao; Wang, Zhi; Kapteijn, Freek; Liu, Xinlei

DOI 10.1021/jacs.1c10192

Publication date 2021 **Document Version** Accepted author manuscript

Published in Journal of the American Chemical Society

Citation (APA)

Cong, S., Yuan, Y., Wang, J., Wang, Z., Kapteijn, F., & Liu, X. (2021). Highly Water-Permeable Metal-Organic Framework MOF-303 Membranes for Desalination. *Journal of the American Chemical Society*, 143(48), 20055-20058. https://doi.org/10.1021/jacs.1c10192

Important note

To cite this publication, please use the final published version (if applicable). Please check the document version above.

Copyright Other than for strictly personal use, it is not permitted to download, forward or distribute the text or part of it, without the consent of the author(s) and/or copyright holder(s), unless the work is under an open content license such as Creative Commons.

Takedown policy

Please contact us and provide details if you believe this document breaches copyrights. We will remove access to the work immediately and investigate your claim.

Highly Water-Permeable Metal–Organic Framework MOF-303 Membranes for Desalination

Shenzhen Cong, Ye Yuan, Jixiao Wang, Zhi Wang, Freek Kapteijn, Xinlei Liu*

ABSTRACT: New membrane materials with excellent water permeability and high ion rejection are needed. Metal-organic frameworks (MOFs) are promising candidates by virtue of their diversity in chemistry and topology. Here, continuous aluminum MOF-303 membranes are prepared on α -Al₂O₃ substrates *via* an *in-situ* hydrothermal synthesis method. The membranes exhibit satisfying rejection of divalent ions (for example, 93.5% and 96.0% for MgCl₂ and Na₂SO₄, respectively) on the basis of size sieving and electrostatic repulsion mechanism and unprecedented permeability (3.0 L·m⁻²·h⁻¹·bar⁻¹·µm). The water permeability outperforms typical zirconium MOF, zeolite, commercial polymeric reverse osmosis and nanofiltration membranes. Additionally, the membrane material exhibits good stability and low production costs. These merits recommend MOF-303 as a next-generation membrane material for water softening.

Metal-organic frameworks (MOFs) are a family of porous crystalline materials composed of inorganic metal ions or metal clusters connected by organic ligands *via* coordination bonds.¹⁻⁴ Given by their diversity in chemistry and topology, MOFs have been extensively explored for applications such as gas storage, separation, sensing, catalysis, proton conduction, *etc.*⁵⁻⁷ Significant progresses have been made on fabricating polycrystalline MOF membranes, especially for gas separations.⁸⁻¹³ However, applications of polycrystalline MOF membranes in water treatment were initially obstructed due to the lack of chemical stability. Although highly water-stable zirconium MOF membranes were unveiled in recent years, ^{14, 15} the related research is still in its infancy. Highly water-permeable MOF membranes with satisfying rejection had been on demand.

Very recently, a water-stable aluminum MOF named MOF-303 (Al(OH)(HPDC); HPDC, 1H-pyrazole-3,5-dicarboxylate) was reported.^{16, 17} It has the *xhh* topology and is constructed from an infinite, rod-like Al(OH)(-COO)₂ clusters linked through HPDC ligands (Figure S1). In the clusters, octahedrally-coordinated Al(III) are corner-shared bound by four bridging carboxyl and two hydroxyl groups. MOF-303 features a 3D framework with 1D rhombic channels (open space around 0.6 nm) along a-axis.¹⁶ The clusters and ligands endow the 1D channels with hydrophilic sites. The high pore volume together with the hydrophilic nature of the framework was translated into impressive water capacity. Besides, fast sorption kinetics were observed attributed to the 1D hydrophilic channels which created a favorable situation for the formation of well-defined water cluster structures.^{17, 18} Furthermore, the pore opening size of the 1D channels is around 0.60 nm in diameter, locating between the diameters of water molecules (0.28 nm, **Table S1**) and common hydrated ions (≥ 0.66 nm, Table S1).¹⁹ Therefore, water desalination can be realized based on the size exclusion mechanism (Figure 1). Additionally, cheap metal and ligand sources are available and water can be used as solvent for the production of MOF-303. The above merits of MOF-303 satisfy the prerequisites of a highperformance membrane material for water desalination to mitigate the shortage of fresh water. However, to the best of our knowledge, no dense polycrystalline MOF-303 membranes have been unveiled.

In this work, to harness these properties inside energyefficient membranes, continuous polycrystalline MOF-303 membranes supported on porous alumina disks were fabricated *via* an *in-situ* hydrothermal synthesis method. The assynthesized membranes exhibited high rejection for divalent ions and unprecedented permeability, recommending MOF-303 as an excellent membrane material for water softening.



Figure 1. Schematic representation of water desalination with a metal–organic framework MOF-303 membrane.

Stability of MOF-303 powders in saline water was tested before membrane fabrication. MOF-303 powders were suspended in various saline aqueous solutions (0.10



Figure 2. Top view (a) and cross-sectional (b) SEM images of a MOF-303 membrane. A dash line is shown in Figure b to distinct the membrane layer and substrate. (c) XRD patterns of experimental MOF-303 powders and membrane. The simulated one is provided for comparison.

wt. % KCl, NaCl and MgCl₂) at 50 °C. The concentration of MOF-303 in these solutions was relatively low (0.04 wt. %) and adequate water solutions were used in case the stability is concentration-dependent.¹⁸ After 50 days' treatment, both the crystalline structure and morphology of MOF-303 were well retained as evidenced by the XRD patterns and SEM images, respectively (**Figures S**3 and S4).

Since no recipes for fabricating polycrystalline MOF-303 membranes were disclosed, the amount of metal source, ligand, alkali and solvent, temperature, duration and the type and roughness of substrates were thoroughly studied in this work to yield sufficient growth nuclei and form fairly well-intergrown membrane structures. Finally, an optimal recipe obtained (see details in the Supporting Information): the molar ratio of Al³⁺:H₃PDC:NaOH:H₂O was fixed at 1:1:2:2000; the proper temperature and duration were 100 °C and 48 h, respectively; porous α-Al₂O₃ disks with asymmetric configuration (70 nm average pore size for the top layer) were preferred as substrates. Porous alumina was employed as substrate, which has been widely used in commercial crystalline zeolite membrane modules, because of its low transport resistance, easy scaling up, and good chemical and fantastic thermal stability. In addition, the surface of the alumina substrate can partially dissolve under alkaline conditions and the released Al will coordinate with HPDC ligands, facilitating the nucleation and growth of MOF-303 membranes.

As indicated in **Figures** 2a and 2b, the surface of the substrate is completely covered with well-intergrown crystals with no visible cracks or pinholes. The crystals have sharp edges with size between 1.0-4.0 μ m yielding a membrane thickness of around 4.0 μ m. The crystalline structure and random packing of the grains were confirmed by the XRD patterns (**Figure** 2c).

To confirm the integrity of the as-synthesized membrane, single-gas permeation measurements were performed with a

soap-film flowmeter at room temperature (25 ± 2 °C) under a transmembrane pressure of 1.0 bar (see details in the Supporting Information). As shown in Figure 3, the H₂ permeance is about $1.2 \times 10^{-6} \text{ mol} \cdot \text{m}^{-2} \cdot \text{s}^{-1} \cdot \text{Pa}^{-1}$ and the ideal selectivity for light gas pairs (6.3, 3.9 and 2.9 for H2/CO2 H2/N2 and H2/CH4, respectively.) is close to the corresponding Knudsen diffusion ratio (4.7, 3.7 and 2.8). Size sieving effect is illustrated by the H₂/C₃H₈ and H₂/i-butane pairs with ideal selectivity of 21.8 and 49.6 and Knudsen diffusion ratio of 4.7 and 5.4, respectively. These results verify that the polycrystalline membrane is continuous, highlighting its integrity. No sharp cut-off between H₂ and other gases was observed probably because the pore size of MOF-303 (~ 0.60 nm) is larger than their kinetic diameters $(H_2, CO_2, N_2, CH_4, C_3H_8 \text{ and } i\text{-butane are } \sim 0.29, 0.33, 0.36,$ 0.38, 0.42 and 0.50 nm, respectively).²⁰ The fluctuation of gas permeance with kinetic diameter can be rationalized on the interplay of adsorption and diffusion effects.

The continuous MOF-303 membrane was applied for water desalination. Five different salt solutions (containing KCl, NaCl, CaCl₂, MgCl₂ and Na₂SO₄) with the same concentration (0.10 wt. %) were prepared as feed. The measurements were carried out in a dead-end system (**Figure** S7) at room temperature $(25 \pm 2 \, ^{\circ}C)$ with a transmembrane pressure of 5.0 bar. Each salt passed through the membrane in a manner of ion pair to conserve electroneutrality. The membrane rejection for different salts was determined by testing the ion conductivity in the retentate and permeate with a conductivity meter. The permeance was obtained based on the permeated volume, membrane area, duration of permeate collection and transmembrane pressure (See details in the Supporting Information).



Figure 3. Single gas permeance and ideal selectivity of a MOF-303 membrane. The operation temperature was 25 ± 2 °C under a pressure difference of 1.0 bar. The pressure of the permeate side was kept under ambient condition.



Figure 4. (a) MOF-303 membrane separation performance for water desalination. The feed concentration of each solution (KCl, NaCl, CaCl₂, MgCl₂ and Na₂SO₄) was 0.1 wt. %. The operation temperature and transmembrane pressure were 25 ± 2 °C and 5.0 bar, respectively. The system was flushed with DI water and dried when feed was changed. (b) Desalination (Mg²⁺retention) performance of MOF-303, zeolite, commercial polymeric reverse osmosis (RO) and nanofiltration (NF) and other MOF membranes. The Figure b was plotted using the data in Table S3.

As depicted in **Figure 4**a, the membrane rejection roughly increases with hydrated ion diameter (in nm, K^+ (0.66) = Cl⁻ $(0.66) < Na^+ (0.72) < SO_4^{2-} (0.76) < Ca^{2+} (0.82) < Mg^{2+} (0.86)),$ demonstrating a size sieving mechanism. The rejection of monovalent ions (33.2% and 35.1% for NaCl and KCl, respectively.) is lower than expected. This can be interpreted by the structural flexibility of MOF-303. Although the pore size of MOF-303 is around 0.60 nm estimated from crystallographic data,¹⁶ an average pore size of 0.80 nm was derived from our Ar adsorption experiment (Figure S5).²¹ Hence, good rejection was achieved in the case of divalent ions (93.5% and 96.0% for MgCl₂ and Na₂SO₄, respectively.) when their hydrated ion diameters are close to 0.80 nm. These results further prove the membrane integrity. As rearrangement and dehydration of the water shell surrounding ions could take place during transport, reducing their effective size, a small amount of divalent ions were present in the permeate. Moreover, the flexibility of MOF-303 framework also account for this phenomenon. Although the hydrated ion diameter of SO₄²⁻ is smaller than Ca²⁺ and Mg²⁺, the rejection for Na₂SO4 is higher than CaCl₂ and MgCl₂. This can be rationalized on the electrostatic repulsion effect. Carboxyl groups in the ligands of MOF-303 can be ionized thus endows the membrane surface with negative charges (Figure S7). The membrane exhibited a moderate permeance (0.74) $L \cdot m^{-2} \cdot h^{-1} \cdot bar^{-1}$). Over the 60 h's evaluation, the permeance was well maintained. Furthermore, a constant ion rejection can be recognized from the repeated tests using MgCl₂ solutions (**Figure** 3a). These indicate that the crystalline structure and grain boundaries of the membrane, the interfaces between the membrane and substrate and the substrate were not damaged during the test. Direct evidences can be found from the invariable SEM images (**Figure** S8) and XRD pattern (**Figure** S9). An outstanding stability and qualified mechanical strength were proved.

In order to benchmark and compare the intrinsic performance of membrane materials, membrane thickness was normalized and permeability was calculated. As anticipated, the MOF-303 membrane delivers the highest permeability (3.0 $L \cdot m^{-2} \cdot h^{-1} \cdot bar^{-1} \cdot \mu m$) combined with satisfying rejection (for Mg^{2+}) (Figure 4b and Table S2). The exceptional water permeability is 3.6, 5.7, 1.9, 3.4 times of the reported typical zirconium MOF UiO-66,15 zeolite MFI,22 commercial polymeric reverse osmosis²³⁻²⁵ and nanofiltration membranes,^{23,} ²⁵⁻²⁷ respectively. This can be attributed to the high water capacity and fast water sorption kinetics of MOF-303.¹⁷ The hydrophilic 1D channels in MOF-303 could create a favorable situation for the formation of well-defined water cluster structures facilitating water transport.18 The high water permeability, satisfying rejection for divalent ions, low material cost together with good stability and reproducibility (Table S2) point that MOF-303 is a promising next-generation membrane material for water softening.

In conclusion, continuous polycrystalline MOF-303 membranes were fabricated on porous α -Al₂O₃ substrates via an in-situ hydrothermal synthesis approach. The as-synthesized membranes exhibited a high rejection of divalent ions (93.5% and 96.0% for MgCl₂ and Na₂SO₄, respectively.) and an unprecedented water permeability (3.0 $L \cdot m^{-2} \cdot h^{-1} \cdot bar^{-1} \cdot \mu m$). The high water capacity and fast water sorption kinetics played an important role in this exceptional water permeability. Furthermore, the membranes feature excellent stability, good stability and low material cost. These properties indicate that MOF-303 is a promising membrane material for water softening. Since MOF membranes with thickness down to a few tens of nanometers were successfully produced via a scalable route, it can be envisaged that, after this earliest report, there will be some optimal preparation conditions for fabricating supported high-flux MOF-303 membranes with thinner selective layer for practical applications.

ASSOCIATED CONTENT

Supporting Information.

Experimental and characterization details; structure of MOF-303; N_2 adsorption-desorption isotherms, SEM images and XRD patterns of MOF-303 powders and membranes, gas separation performance, water desalination performance. This material is available free of charge via the Internet at <u>http://pubs.acs.org</u>.

AUTHOR INFORMATION

Corresponding Author

Xinlei Liu – Chemical Engineering Research Center, School of Chemical Engineering and Technology, Tianjin Key Laboratory of Membrane Science and Desalination Technology, State Key Laboratory of Chemical Engineering, Tianjin University, 300072 Tianjin, China; Email: xinlei_liu1@tju.edu.cn

Authors

Shenzhen Cong – Chemical Engineering Research Center, School of Chemical Engineering and Technology, Tianjin Key Laboratory of Membrane Science and Desalination Technology, State Key Laboratory of Chemical Engineering, Tianjin University, 300072 Tianjin, China

Ye Yuan – Chemical Engineering Research Center, School of Chemical Engineering and Technology, Tianjin Key Laboratory of Membrane Science and Desalination Technology, State Key Laboratory of Chemical Engineering, Tianjin University, 300072 Tianjin, China

Jixiao Wang – Chemical Engineering Research Center, School of Chemical Engineering and Technology, Tianjin Key Laboratory of Membrane Science and Desalination Technology, State Key Laboratory of Chemical Engineering, Tianjin University, 300072 Tianjin, China

Zhi Wang – Chemical Engineering Research Center, School of Chemical Engineering and Technology, Tianjin Key Laboratory of Membrane Science and Desalination Technology, State Key Laboratory of Chemical Engineering, Tianjin University, 300072 Tianjin, China

Freek Kapteijn – Catalysis Engineering, Chemical Engineering Department, Delft University of Technology, 2629 HZ Delft, The Netherlands

Notes

The authors declare no competing financial interest.

ACKNOWLEDGMENT

We acknowledge the valuable input from Prof. Y. Zhang at ShanghaiTech University. This work was supported by National Natural Science Foundation of China (22008171) and Peiyang Scholars Program (Tianjin University).

REFERENCES

(1) Zhou, H.-C.; Long, J. R.; Yaghi, O. M. Introduction to metalorganic frameworks. *Chem. Rev.* 2012, *112*, 673-674.

(2) Kitagawa, S. Metal–organic frameworks (MOFs). *Chem. Soc. Rev.* **2014**, *43*, 5415-5418.

(3) Maurin, G.; Serre, C.; Cooper, A.; Férey, G. Themed collection Metal-organic frameworks and porous polymers–current and future challenges. *Chem. Soc. Rev.* **2017**, *46*, 3104-3107.

(4) Dincă, M.; Long, J. R. Introduction: porous framework chemistry. *Chem. Rev.* **2020**, *120*, 8037-8038.

(5) Furukawa, H.; Cordova, K. E.; O'Keeffe, M.; Yaghi, O. M. The chemistry and applications of metal-organic frameworks. *Science* **2013**, *341*.

(6) Freund, R.; Canossa, S.; Cohen, S. M.; Yan, W.; Deng, H.; Guillerm, V.; Eddaoudi, M.; Madden, D. G.; Fairen-Jimenez, D.; Lyu,

H.; Macreadie, L. K.; Ji, Z.; Zhang, Y.; Wang, B.; Haase, F.; Woll, C.; Zaremba, O.; Andreo, J.; Wuttke, S.; Diercks, C. S. 25 years of reticular chemistry. *Angew. Chem. Int. Ed.* **2021** (DOI: 10.1002/anie.202101644).

(7) Freund, R.; Zaremba, O.; Arnauts, G.; Ameloot, R.; Skorupskii, G.; Dinca, M.; Bavykina, A.; Gascon, J.; Ejsmont, A.; Goscianska, J.; Kalmutzki, M.; Lachelt, U.; Ploetz, E.; Diercks, C.; Wuttke, S. The current status of MOF and COF applications. *Angew. Chem. Int. Ed.* **2021** (DOI: 10.1002/anie.202106259).

(8) Ma, X.; Kumar, P.; Mittal, N.; Khlyustova, A.; Daoutidis, P.; Mkhoyan, K. A.; Tsapatsis, M. Zeolitic imidazolate framework

membranes made by ligand-induced permselectivation. *Science* **2018**, *361*, 1008-1011.

(9) Peng, Y.; Li, Y.; Ban, Y.; Jin, H.; Jiao, W.; Liu, X.; Yang, W. Metalorganic framework nanosheets as building blocks for molecular sieving membranes. *Science* **2014**, *346*, 1356-1359.

(10) Knebel, A.; Geppert, B.; Volgmann, K.; Kolokolov, D.; Stepanov, A.; Twiefel, J.; Heitjans, P.; Volkmer, D.; Caro, J. Defibrillation of soft porous metal-organic frameworks with electric fields. *Science* **2017**, *358*, 347-351.

(11) Brown, A. J.; Brunelli, N. A.; Eum, K.; Rashidi, F.; Johnson, J.; Koros, W. J.; Jones, C. W.; Nair, S. Interfacial microfluidic processing of metal-organic framework hollow fiber membranes. *Science* **2014**, *345*, 72-75.

(12) Qian, Q.; Asinger, P. A.; Lee, M. J.; Han, G.; Mizrahi Rodriguez, K.; Lin, S.; Benedetti, F. M.; Wu, A. X.; Chi, W. S.; Smith, Z. P. MOFbased membranes for gas separations. *Chem. Rev.* **2020**, *120*, 8161-8266.

(13) Denny, M. S.; Moreton, J. C.; Benz, L.; Cohen, S. M. Metal – organic frameworks for membrane-based separations. *Nat. Rev. Mater.* **2016**, *1*, 16078.

(14) Liu, X.; Demir, N. K.; Wu, Z.; Li, K. Highly water-stable zirconium metal-organic framework UiO-66 membranes supported on alumina hollow fibers for desalination. *J. Am. Chem. Soc.* **2015**, *137*, 6999-7002.

(15) Wang, X.; Zhai, L.; Wang, Y.; Li, R.; Gu, X.; Yuan, Y. D.; Qian, Y.; Hu, Z.; Zhao, D. Improving water-treatment performance of zirconium metal-organic framework membranes by postsynthetic defect healing. *ACS Appl. Mater. Interfaces* **2017**, *9*, 37848-37855.

(16) Fathieh, F., Kalmutzki, M. J., Kapustin, E. A., Waller, P. J., Yang, J., Yaghi, O. M. Practical water production from desert air. *Sci. Adv.* **2018**, *4*, eaat3198.

(17) Hanikel, N.; Prevot, M. S.; Fathieh, F.; Kapustin, E. A.; Lyu, H.; Wang, H.; Diercks, N. J.; Glover, T. G.; Yaghi, O. M. Rapid cycling and exceptional yield in a metal-organic framework water harvester. *ACS Cent. Sci.* **2019**, *5*, 1699-1706.

(18) Liu, X.; Wang, X.; Kapteijn, F. Water and metal-organic frameworks: From interaction toward utilization. *Chem. Rev.* **2020**, *120*, 8303-8377.

(19) Xu, S.; Song, J.; Bi, Q.; Chen, Q.; Zhang, W.-M.; Qian, Z.; Zhang, L.; Xu, S.; Tang, N.; He, T. Extraction of lithium from Chinese saltlake brines by membranes: Design and practice. *J. Membr. Sci.* **2021**, *635*, 119441.

(20) Breck, D. W., Zeolite molecular sieves: structure, chemistry and use. John Wiley & Sons, Inc.: New York,: 1974.

(21) Wang, H.; Shi, Z.; Yang, J.; Sun, T.; Rungtaweevoranit, B.; Lyu, H.; Zhang, Y. B.; Yaghi, O. M. Docking of Cu(I) and Ag(I) in metalorganic frameworks for adsorption and separation of xenon. *Angew. Chem. Int. Ed. Engl.* **2021**, *60*, 3417-3421.

(22) Zhu, B.; Myat, D. T.; Shin, J.-W.; Na, Y.-H.; Moon, I.-S.; Connor, G.; Maeda, S.; Morris, G.; Gray, S.; Duke, M. Application of robust MFI-type zeolite membrane for desalination of saline wastewater. *J. Membr. Sci.* **2015**, *475*, 167-174.

(23) Freger, V.; Gilron, J.; Belfer, S. TFC polyamide membranes modified by grafting of hydrophilic polymers: an FT-IR/AFM/TEM study. *J. Membr. Sci.* **2002**, *209*, 283-292.

(24) Garcia, F.; Ciceron, D.; Saboni, A.; Alexandrova, S. Nitrate ions elimination from drinking water by nanofiltration: Membrane choice. *Sep. Purif. Technol.* **2006**, *52*, 196-200.

(25) Freger, V. Swelling and morphology of the skin layer of polyamide composite membranes: an atomic force microscopy study. *Environ. Sci. Technol.* **2004**, *38*, 3168-3175.

(26) Mohammad, A. W.; Teow, Y. H.; Ang, W. L.; Chung, Y. T.; Oatley-Radcliffe, D. L.; Hilal, N. Nanofiltration membranes review: Recent advances and future prospects. *Desalination* **2015**, *356*, 226-254.

(27) Boo, C.; Wang, Y.; Zucker, I.; Choo, Y.; Osuji, C. O.; Elimelech, M. High performance nanofiltration membrane for effective removal of perfluoroalkyl substances at high water recovery. *Environ. Sci. Technol.* **2018**, *52*, 7279-7288.