

Delft University of Technology

Impact of high temperature $\rm H_2$ pre-treatment on Pt-AlGaN/GaN HEMT sensor for $\rm H_2S$ detection

Zhang, Jian; Sokolovskij, Robert; Chen, Ganhui; Zhu, Yumeng; Qi, Yongle; Lin, Xinpeng; Li, Wenmao; Zhang, Guo Qi; Jiang, Yu-Long; Yu, Hongyu **DOI**

10.1016/j.snb.2018.10.052

Publication date 2019 Document Version Accepted author manuscript Published in Sensors and Actuators, B: Chemical

Citation (APA)

Zhang, J., Sokolovskij, R., Chen, G., Zhu, Y., Qi, Y., Lin, X., Li, W., Zhang, G. Q., Jiang, Y.-L., & Yu, H. (2019). Impact of high temperature H pre-treatment on Pt-AlGaN/GaN HEMT sensor for H S detection. *Sensors and Actuators, B: Chemical*,²280, 138-143. https://doi.org/10.1016/j.snb.2018.10.052

Important note

To cite this publication, please use the final published version (if applicable). Please check the document version above.

Copyright

Other than for strictly personal use, it is not permitted to download, forward or distribute the text or part of it, without the consent of the author(s) and/or copyright holder(s), unless the work is under an open content license such as Creative Commons.

Takedown policy

Please contact us and provide details if you believe this document breaches copyrights. We will remove access to the work immediately and investigate your claim.

Accepted Manuscript

Title: Impact of high temperature H_2 pre-treatment on Pt-AlGaN/GaN HEMT sensor for H_2S detection

Authors: Jian Zhang, Robert Sokolovskij, Ganhui Chen, Yumeng Zhu, Yongle Qi, Xinpeng Lin, Wenmao Li, Guo Qi Zhang, Yu-Long Jiang, Hongyu Yu



PII:	S0925-4005(18)31815-X
DOI:	https://doi.org/10.1016/j.snb.2018.10.052
Reference:	SNB 25486
To appear in:	Sensors and Actuators B
Received date:	8-4-2018
Revised date:	9-10-2018
Accepted date:	9-10-2018

Please cite this article as: Zhang J, Sokolovskij R, Chen G, Zhu Y, Qi Y, Lin X, Li W, Qi Zhang G, Jiang Y-Long, Yu H, Impact of high temperature H₂ pre-treatment on Pt-AlGaN/GaN HEMT sensor for H₂S detection, *Sensors and amp; Actuators: B. Chemical* (2018), https://doi.org/10.1016/j.snb.2018.10.052

This is a PDF file of an unedited manuscript that has been accepted for publication. As a service to our customers we are providing this early version of the manuscript. The manuscript will undergo copyediting, typesetting, and review of the resulting proof before it is published in its final form. Please note that during the production process errors may be discovered which could affect the content, and all legal disclaimers that apply to the journal pertain.

Impact of high temperature H₂ pre-treatment on Pt-AlGaN/GaN HEMT sensor for H₂S detection

Jian Zhang^{a,b,c,1}, Robert Sokolovskij^{b,d,e,1}, Ganhui Chen^{b,c}, Yumeng Zhu^{b,c}, Yongle Qi^{b,c}, Xinpeng Lin^{b,c}, Wenmao Li^{b,c}, Guo Qi Zhang^d, Yu-Long Jiang^{a*}, Hongyu Yu^{b,c*}

^a State Key Laboratory of ASIC and System, School of Microelectronics, Fudan University, 200433 Shanghai, China

^b Department of Electrical and Electronic Engineering, Southern University of Science and Technology, 518055, Shenzhen, China;

^c Shenzhen Key Laboratory of the Third Generation Semi-conductor, 518055 Shenzhen, China

^d Department of Microelectronics, Delft University of Technology, 2628 CD Delft, the Netherlands

^e State Key Laboratory of Solid State Lighting, 213161 Changzhou, China

*Email addresses of corresponding authors: yljiang@fudan.edu.cn (Y. L. Jiang), yuhy@sustc.edu.cn

(H. Y. Yu)

¹ These authors contributed equally to this work

Highlights:

- A H₂ gas flow pre-treatment at high temperature is utilized for Pt-AlGaN/GaN HEMT H₂S sensors
- The detection concentration range of H₂S is extended after pre-treatment
- The linearity of Pt-HEMT sensors is improved after pre-treatment
- The mechanism behind pre-treatment is discussed and characterized

Abstract:

In this paper, a method to extend the detection range of hydrogen sulfide (H₂S) gas sensor is demonstrated. The sensor is based on AlGaN/GaN high electron mobility transistors (HEMTs) with Pt gate. It is observed that the as-fabricated devices exhibited sensing signal saturation at 30 ppm H₂S exposure in dry air. A pre-treatment using H₂ pulses in dry air ambient at 250 °C was applied to extend the detection range of the sensor. The H₂ treated H₂S gas sensor was able to detect a higher

H₂S concentration up to 90 ppm at 250 °C without complete saturation.

Key words: AlGaN/GaN; Pt; HEMT; H₂S; Gas Sensor

1. Introduction

 H_2S is colorless gas with the foul smell of rotten eggs. It can be emitted by many industrial activities, such as petroleum refining or paper mills [1]. Besides, it is a broad-spectrum poison and can severely affect the nervous system. Only 20 ppm H_2S is the acceptable ceiling concentration established by the Occupational Safety and Health Administration (OSHA) [2]. For 100-150 ppm H_2S , it can paralyze the olfactory nerve, and then the sense of smell will disappear [1]. Therefore, it is necessary to detect H_2S within low tens up to at least 100 ppm.

There are many ways to detect H_2S , such as metal-oxide semiconductor (MOS) [1, 3], electrochemical [4], Schottky diode [5] and field effect transistor sensors [6, 7]. Because industrial activity is one of the largest sources of H_2S , harsh environments like high temperature should be taken into consideration. Due to the wide bandgap, high chemical stability and corrosion resistance, the compound semiconductors like GaN [8, 9] and SiC [10, 11] have gained many interests. Compared with Schottky diode sensors, the transistor-based sensors usually have a larger sensing current and a higher signal-to-noise ratio. Especially for AlGaN/GaN based HEMT [12, 13], due to the presence of two-dimensional electron gas (2DEG), the response current is even larger than mA level.

Previously, Darmastuti et al. had fabricated a H_2S sensor based on SiC field effect transistor (FET) with Pt or Ir gate [10]. The device exhibited saturation at a low concentration of approximately 10 ppm, which is similar to our as-fabricated sensors. No pre-treatment was reported for their sensors. It was also demonstrated that the as-fabricated Pt-SiC MOS sensors showed little or no H_2 gas response [14]. In order to activate sensors, alternated exposures of 1% O_2 in N_2 (5 min) and 10% H_2 in N_2 (3 min) for 7 h at 610 °C were once applied [14].

In this work, we report on the H_2 related pre-treatment for H_2S gas sensors based on the AlGaN/GaN HEMT. It clearly shows the effective extension of H_2S detection range.

2. Experimental

Fig. 1 (a) shows the cross-sectional view of our HEMT-sensors. The devices were fabricated on 2-inch sapphire wafers with epitaxial stacks grown by MOCVD. The epitaxial stacks started with a nucleation layer in order to reduce the lattice mismatch. Then it was followed by a 1.8 μ m GaN buffer layer, a 1 nm AlN interlayer, an unintentionally doped 21 nm Al_{0.26}Ga_{0.74}N barrier layer and a 1 nm GaN capping layer. The mesa etching was performed by BCl₃/Cl₂ plasma to isolate devices. Then a Ti/Al/Ti/Au (20/110/40/50 nm) stack was deposited on source/drain by e-beam evaporation and patterned by lift-off method. Annealing at 870 °C for 47 s in N₂ ambient was performed to form Ohmic contacts. Next, the sensing gate electrode was formed by e-beam evaporation of a 10 nm Pt layer. Gate pattern was also defined by lift-off process. The bi-layer of 30/300 nm Ti/Au was also fabricated by lift-off process as wire bonding metal. The devices were passivated by 500 nm SiN_x using PECVD. Finally, Pt gate area was opened to detect the gas. The gate dimension exposed to gas was 40 μ m × 400 μ m (length × width) and the spacing between gate and source/drain was 6 μ m [15].

The as-fabricated sensors were annealed at 150 °C in dry air for 48 hours to test sensors' thermal stability. The sensors with no performance degradation were used for the formal measurement. A commercial gas mixing system was employed for H₂S sensing and H₂ pre-treatment. A stable gas flow at a rate of 310 sccm was continuously introduced into a 1.8 L chamber. H₂S or H₂ gas in dry synthetic air background with different concentration was used. The humidity in chamber was kept at 0% RH for all the measurements to inhibit moisture influence. For H₂ pre-treatment, the samples were exposed to alternated gas flows of dry air (50 min) and H₂ (20 min) for 6 hours at 250 °C. The concentration of H₂ was increased with each exposure from 100 ppm to 900 ppm at 300 ppm increment. The electrical signals were measured by a pair of Keithley 2450 source meters with the measurement temperature varying from room temperature to 300 °C. After each measurement cycle, the sensors were reset under room ambient conditions for at least 12 hours. Atomic force microscopy (AFM) was utilized to analyze the Pt gate surface morphology before and after H₂ pre-treatment.

3. Results and discussion

3.1 As-fabricated sensors

Our previous studies have shown that the sensor can operate from 150 to 250 °C, and the best performance is obtained at an operation temperature of 250 °C [16]. Fig. 1 (b) shows the output curves of a HEMT sensor exposed to 15 ppm H₂S gas at 250 °C. Obviously, it shows linear and saturation regions with a pinch-off voltage of -3 V (gate-source voltage, V_{GS}). It is a normally-on device due to the 2DEG. When exposed to H₂S gas, the source-drain current I_{DS} increases even at a low concentration of 15 ppm, as shown in Fig. 1(b). The detection mechanism is related with the reaction between gas and catalytic metal Pt. After H₂S is adsorbed on Pt film, the S-H bond is then divided by Pt, resulting in the production of H atom or molecule [5]. Finally, the S atom can react with O₂ to form volatile SO₂ and the H atom can form a dipole layer. The dipole layer can affect the Schottky barrier height between Pt and GaN. Consequently, the threshold voltage and the drain current are altered.

Fig. 2 (a) shows the transient response curves for different H₂S concentrations at 250 °C using a fresh sensor without H₂ pre-treatment. The transient response curves were measured at fixed voltages (V_{GS} =0 V and V_{DS} =5 V). The drain current (I_{DS}) was recorded with a 3s interval. Clearly, I_{DS} is saturated at a low concentration of 30 ppm. With a higher gas concentration, the H₂S atoms will cover larger area of Pt surface. Then the output signal intensity increases. But there is a limit for coverage, which may result in saturation of signal intensity. This phenomenon is similar to other studies based on Pt-SiC field effect transistor [10].

3.2 H₂ pre-treated sensors

Fig. 2 (b) shows the transient response curves for the H₂ pre-treated sensors at 250 °C. The different H₂S concentration is clearly distinguished.

To compare the detection range more quantitatively, the gas response is calculated by

$$S(\%) = \frac{\Delta I_{DS}}{I_{DS,air}} \times 100\%,\tag{1}$$

where $\Delta I_{DS} = I_{DS,H_2S} - I_{DS,air}$ is the drain current variation between H₂S and air ambient. Fig. 3 (a) shows the gas response to H₂S for sensors with and without H₂ pre-treatment. Without H₂ pretreatment, the gas response is nearly unchanged for different H₂S concentration. While, with H₂ pretreatment it's almost linear. The large difference indicates that the H₂ pre-treatment can effectively improve sensor performance by extending its detection range.

Before sensing H_2S , the influence of H_2 pre-treatment on sensors is summarized in Fig 3(b) - (d). As shown in Fig. 3 (b), the H_2 pre-treatment obviously makes the drain current become smaller. The expression of drain current in saturation region is,

$$I_{DSS} = \frac{\mu C_b W_g}{2L_g} (V_{GS} - V_{TH})^2,$$
(2)

where μ is the 2DEG mobility, W_g/L_g is the ratio of gate width to length, C_b is the sum of capacitance contributions from each layer between the gate metal and 2DEG $(1/C_b = 1/C_{GaN} + 1/C_{AlGaN} + 1/C_{AlN} + 1/C_{2DEG})$. Threshold voltage (V_{TH}) in this work is extracted from $\sqrt{I_{DS}} - V_{GS}$ curve biased in the saturation region [17]. The V_{TH} shift can be observed in Fig. 3 (c), which shows a positive shift and results in I_{DS} and transconductance g_m reduction. Fig. 3 (d) is the extracted I_{DS} shift and V_{TH} shift at different measurement temperature. At a higher measurement temperature, the V_{TH} shift decreases and the I_{DS} shift is smaller too. The expression of V_{TH} for an AlGaN/GaN HEMT is [18],

$$V_{TH} = \Phi_b - \frac{\Delta E_c}{q} - \frac{qn_s}{c_b},\tag{3}$$

where Φ_b is the Schottky barrier height, ΔE_c is the conduction band discontinuity, q is the electron charge and n_s is the sheet charge carrier density. The Schottky barrier height is dependent on the work function (Φ_m) of the gate metal and the semiconductor electron affinity (χ_s) , i.e., $\Phi_b = \Phi_m - \chi_s$. Therefore, we believe the shift of V_{TH} should be related to the work function variation of the gate metal.

3.3 Explanation

For the V_{TH} positive shift after H₂ pre-treatment, there are three possible reported mechanisms [19]: a) the adsorbed H atoms give rise to a dipole layer; b) the existence of slow H trapping sites; and c) the lattice expansion due to H induced stress. The dipole layer is reversible and decreases the V_{TH} [20-22]. The existence of slow H trapping sites is also called Hydrogen-Induced Drift (HID), which is related to the metal-insulator interface [19, 23]. It is not temporary but it can decrease the V_{TH} . According to previous studies [19, 24], the stress induced by H can change the metal lattice parameters. Besides, it can even loosen contact between metal and substrate [24]. However, we didn't find any difference of sensor after H₂ pre-treatment by microscope. The AFM measurements shown in Fig. 4 also clearly indicate little change on Pt film. So, a), b) and c) cannot explain our

experimental results.

A new mechanism is proposed in this paper. Fig. 5 (a) and (b) show the H existence status in Pt gate for sensors with and without H₂ pre-treatment. There will be two statuses of H atoms within Pt film. One is trapped by the body defects in the Pt grains, losing its electron and existing as fixed positive H⁺ ions. Then the induced negative charges will accumulate on Pt film surface as shown in Fig. 5(b). These negative charges will increase the work function of Pt film, resulting in the V_{TH} positive shift and I_{DS} reduction as mentioned in section 3.2. Since these H⁺ ions within Pt grains are fixed, these induced negative charges on Pt film surface are also stable. So there is a larger V_{TH} for these transistors with H₂ pre-treatment as shown in Fig. 3(b). The other status of H is related with absorption by Pt surface defects [25], such as surface clusters, steps and grain boundaries. Once absorbed, H atoms will show positive polarity due to a weaker electronegativity comparing with Pt. Thus, a dipole layer may form around the Pt film surface and grain boundaries as shown in Fig. 5(c) [19]. These dipole layers will equivalently lower the Pt film work function, which will reduce the V_{TH} , as calculated in equation (3). However, these absorbed H atoms are not stable, they can diffuse out into the atmosphere when the sensed H₂ concentration is lower.

Since there are fixed H⁺ ions within the Pt grains after H₂ pre-treatment, the induced negative charges on the Pt film surface and interface will stably exist there. While, the adsorbed H atoms on the Pt top surface will show positive polarity. Thus, the induced negative charges will attract these adsorbed H atoms. Consequently, on the Pt top surface the entrance for the adsorbed H atoms' diffusion into the Pt grain boundaries and interface of Pt/GaN will be partly blocked. The H atoms diffusion velocity at these entrances will be lowered. Hence, with the same sensing condition the amount of H atoms which can finally diffuse into the interface of Pt/GaN will decrease for the same H₂S concentration. So even for 90 ppm H₂S the I_{DS} is still not saturated for the sensor with H₂ pre-treatment. As seen in Fig. 2(b), the I_{DS} for 90 ppm H₂S is less than that for 30 ppm H₂S but without H₂ pre-treatment as shown in Fig. 2(a). Thus, the sensor detection range is extended.

Besides, Fig. 6 shows the transient response curves for samples pre-treated with H₂ at 250 °C. Only after exposure to 900 ppm H₂, the I_{DS} in dry air obviously degrades. It means that the positive H⁺ ions form within the Pt grains, which indicates that it is not easy to form these diffusion induced H⁺ ions. A higher temperature and a higher H₂ concentration are preferred to activate and accelerate

the diffusion process within the grains. Once these H^+ ions form they will be much more stable than those adsorbed H atoms at surface or interface. It also implies the H^+ ions formation process can be ignored when the H_2 concentration is less than 100 ppm.

4. Conclusion:

In this paper, it is demonstrated that the Pt-AlGaN/GaN HEMT can detect H_2S at 250 °C. However, the as-fabricated sensors exhibit saturation for low H_2S concentrations. A high temperature H_2 pre-treatment is proposed and successfully applied to extend the concentration detection range. The mechanism is believed to be correlated with the interaction between Pt film and H_2 , which may introduce stable H^+ ions within Pt grains and result in the V_{TH} positive shift. The negative charges induced by these H^+ ions at the Pt top surface will attract the adsorbed H atoms with positive polarity. This will reduce the diffusion velocity of these adsorbed H atoms, finally decreasing the amount of H related dipoles at Pt/GaN interface. Thus a higher H_2S concentration is required to reach the same saturation level of the dipoles at Pt/GaN interface, which equivalently increases the H_2S concentration detection range.

Acknowledgements

This research was funded by State Key Laboratory of Solid State Lighting, Changzhou base and "Research of low cost fabrication of GaN power devices and system integration" research fund (JCYJ20160226192639004), "Research of AlGaN HEMT MEMS sensor for work in extreme environment" (JCYJ20170412153356899), "Research of the reliability mechanism and circuit simulation of GaN HEMT" (2017A050506002), and Natural Science Foundation of China (61874030).

Reference:

[1] K. Wetchakun, T. Samerjai, N. Tamaekong, C. Liewhiran, C. Siriwong, V. Kruefu, A. Wisitsoraat,
A. Tuantranont, S. Phanichphant, Semiconducting metal oxides as sensors for environmentally
hazardous gases, Sens. & Actuators B, 160 (2011) 580-591.
https://doi.org/10.1016/j.snb.2011.08.032

[2] Chou, Toxicological profile for hydrogen sulfide and carbonyl sulfide, Environ. Pollutants/toxicity, (2014). https://stacks.cdc.gov/view/cdc/43468

[3] K. Zakrzewska, Mixed oxides as gas sensors, Thin Solid Films, 391 (2001) 229-238. https://doi.org/10.1016/S0040-6090(01)00987-7

[4] N.S. Lawrence, L. Jiang, T.G. Jones, R.G. Compton, A thin-layer amperometric sensor for hydrogen sulfide: the use of microelectrodes to achieve a membrane-independent response for Clark-type sensors, Analytical Chem., 75 (2003) 2499-2503. https://doi.org/10.1021/ac0206465
[5] J.F. Xiao, C.P. Hsu, I. Sarangadharan, G.Y. Lee, J.I. Chyi, Y.L. Wang, Pt/GaN Schottky Diodes for Highly Sensitive Hydrogen Sulfide Detection, 5 (2016) Q137-Q139. https://doi.org/10.1149/2.0311605jss

[6] I. Lundström, M. Armgarth, A. Spetz, F. Winquist, Gas sensors based on catalytic metal-gate field-effect devices, Sens & Actuators B, 10 (1986) 399-421. https://doi.org/10.1016/0250-6874(86)80056-7

[7] M.S. Shivaraman, Detection of H2S with Pd - gate MOS field - effect transistors, J. Appl. Phys.,
47 (1976) 3592-3593. https://doi.org/10.1063/1.323162

[8] Y. Halfaya, C. Bishop, A. Soltani, S. Sundaram, V. Aubry, P.L. Voss, J.P. Salvestrini, A. Ougazzaden, Investigation of the Performance of HEMT-Based NO, NO₂ and NH₃ Exhaust Gas Sensors for Automotive Antipollution Systems, Sens., 16 (2016) 273. https://doi.org/10.3390/s16030273

[9] J. Song, W. Lu, J.S. Flynn, G.R. Brandes, Pt-AlGaN / GaN Schottky diodes operated at 800°
C for hydrogen sensing, Appl. Phys. Lett., 87 (2005) 4364. https://doi.org/10.1063/1.2058227

[10] Z. Darmastuti, M. Andersson, L. Ojamae, A.L. Spetz, M. Larsson, N. Lindqvist, SiC based
Field Effect Transistor for H2S detection, Sens. IEEE, (2011) 770-773.
https://doi.org/10.1109/ICSENS.2011.6127411

[11] A. Samman, S. Gebremariam, L. Rimai, X. Zhang, J. Hangas, G.W. Auner, Silicon-carbide MOS capacitors with laser-ablated Pt gate as combustible gas sensors, Sens. & Actuators B, 63
(2000) 91-102. https://doi.org/10.1016/S0925-4005(00)00290-2

[12] R. Sokolovskij, J. Zhang; E. Iervolino, C. Zhao, F. Santagata, F. Wang, H. Yu, P. M. Sarro, G.
Q. Zhang, Hydrogen sulfide detection properties of Pt-gated AlGaN/GaN HEMT sensor, Sens. & Actuators B, (2018). under review.

[13] R. Sokolovskij, E. Iervolino, C. Zhao, F. Santagata, F. Wang, H. Yu, P.M. Sarro, G.Q. Zhang,
Pt-AlGaN/GaN HEMT-Sensor for Hydrogen Sulfide (H2S) Detection, 1 (2017) 463.
https://doi.org/10.3390/proceedings1040463

[14] Y.H. Kahng, R.G. Tobin, R. Loloee, R.N. Ghosh, Sulfur surface chemistry on the platinum gate of a silicon carbide based hydrogen sensor, J. Appl. Phys., 102 (2007) 1. https://doi.org/10.1063/1.2779288

[15] R. Sokolovskij, F. Santagata, P. M. Sarro, G. Q. Zhang, E. Iervolino, C. H. Zhao, F. Wang, H.
Y. Yu, Pt-AlGaN/GaN HEMT-sensor layout optimization for enhancement of hydrogen detection, 2017 IEEE sensors,2017. https://10.1109/ICSENS.2017.8234419

[16] R. Sokolovskij, J. Zhang, E. Iervolino, C. Zhao, F. Santagata, F. Wang, H. Y. Yu, P. M. Sarro,G. Q. Zhang, Hydrogen sulfide detection properties of Pt-gated AlGaN/GaN HEMT-sensor. Sens.& Actuators B, 2018, recived.

[17] A. Ortiz-Conde, F.J. Garcia Sanchez, J.J. Liou, A. Cerdeira, M. Estrada, Y. Yue. A review of recent MOSFET threshold voltage extraction methods. Microelectronics Reliability, 42, (2002), 583-596. https://doi.org/10.1016/S0026-2714(02)00027-6

[18] Y. Cai, Y. Zhou, K. M. Lau, K. J. Chen, Control of Threshold Voltage of AlGaN/GaN HEMTs
by Fluoride-Based Plasma Treatment: From Depletion Mode to Enhancement Mode, IEEE
Transactions on Electron Devices 53.9 (2006) 2207-2215.
https://doi.org/10.1109/TED.2006.881054

[19] I. Lundstrom, M. Armgarth, and L. G. Petersson, Physics with catalytic metal gate chemical sensors. Crit. Rev. Solid State Sci., 3 (2006) 201. https://doi.org/10.1080/10408438908243446
[20] C.S. Hsu, H.I. Chen, C.F. Chang, T.Y. Chen, C.C. Huang, P.C. Chou, W.C. Liu, On the hydrogen sensing characteristics of a Pd/AlGaN/GaN heterostructure field-effect transistor (HFET), Sens. &

Actuators B, 165 (2012) 19-23. https://doi.org/10.1016/j.snb.2012.01.059

[21] J.R. Huang, W.C. Hsu, H.I. Chen, W.C. Liu, Comparative study of hydrogen sensing characteristics of a Pd/GaN Schottky diode in air and N2 atmospheres, Sens. & Actuators B, 123 (2007) 1040-1048. https://doi.org/10.1016/j.snb.2006.11.008

[22] M. Safari, M. Gholizadeh, A. Salehi, Modeling and simulation of a MOSFET gas sensor with platinum gate for hydrogen gas detection, Sens. & Actuators B, 141 (2009) 1-6. https://doi.org/10.1016/j.snb.2009.06.032

[23] C. Nylander, M. Armgarth, and C. Svensson, Hydrogen induced drift in palladium gate metal oxide - semiconductor structures. J. Appl. Phys., 56.4 (1984) 1177-1188.
 http://dx.doi.org/10.1063/1.334046

[24] M. Armgarth, and C. Nylander, Blister formation in Pd gate MIS hydrogen sensors, IEEE Electron Device Lett., 3.12 (1982) 384-386. http://dx.doi.org/10.1109/EDL.1982.25608

[25] R. Duś, and E. Nowicka, Bivalent ability for charge transfer in process of hydrogen interaction with surfaces of transition metals, Prog. Surf. Sci., 67 (2001) 139-154. https://doi.org/10.1016/S0079-6816(01)00020-X

Jian Zhang received the B.S. degree from Fudan University, Shanghai, China, in 2015. He is currently pursuing the Ph.D. degree in Fudan University. His current research interests include electrical properties of metal/semiconductor interfaces, and fabrication and characterization of wide bandgap gallium nitride (GaN)-based power electronic devices and chemical sensors.

Robert Sokolovskij received the B.S. degree in electronics engineering from Vilnius University, Vilnius, Lithuania in 2010 and the M.S. degree in electrical engineering from Delft University of Technology, Delft, the Netherlands in 2013, where he is currently working towards his Ph.D degree. From 2014 he is also with the State Key Laboratory of Solid State Lighting, Changzhou, China. From 2018 he is part-time research assistant at Southern University of Science and Technology, Shenzhen, China. His current research interests include design, fabrication and characterization of wide bandgap gallium nitride (GaN)-based power electronic devices and chemical sensors.

Ganhui Chen's biography is not ready at this moment.

Yumeng Zhu's biography is not ready at this moment.

Yongle Qi's biography is not ready at this moment.

Xinpeng Lin's biography is not ready at this moment.

Wenmao Li's biography is not ready at this moment.

Guo Qi Zhang (M'03-F'14) received his Ph.D. degree in aerospace engineering at Delft University of Technology, Delft, the Netherlands, in 1993. He is currently a Chair Professor in the Department of Microelectronics at Delft University of Technology since 2013. His research focuses on heterogeneous micro/nano-electronics packaging, system integration and reliability. Prof. Zhang had been with Philips for 20 years: Principal Scientist (1994-1996), Technology Domain Manager (1996-2005), Senior Director of Technology Strategy (2005-2009), and the Philips Fellow (2009-2013). From 2002, he also had part-time appointments as Professor at Technical University of Eindhoven (2002-2005), and Chair Professor at Delft University of Technology (2005-2013). Prof. Zhang is one of pioneers in developing More than Moore (MtM) strategy when he served as Chair of MtM technology team of Europeans Nanoelectronics Platform (ENIAC) in 2005. Prof. Zhang has published more than 350 papers including more than 140 journal papers, 3 books, and 17 book chapters, and more than 100 patents. He was awarded Outstanding Contributions to Reliability Research by European Center for Micro/Nanoreliability, Berlin in 2007. He received Excellent Leadership Award at EuroSimE and Special Achievement Award at ICEPT. He was elected as IEEE Fellow in 2014, and received IEEE CPMT Outstanding Sustained Technical Contribution Award in 2015.

Yulong Jiang received the B.S. degree in physics in 1999 and the Ph.D. degree in Microelectronics in 2005, both from the Fudan University, Shanghai, China. Since 2005, he has been with the School of Microelectronics at Fudan University, where he has been active in the research and development of metallization engineering of source/drain and gate for advanced CMOS technologies. He has authored/coauthored more than 80 publications.

Hongyu Yu's biography is not ready at this moment.

Figure captions

Fig 1. (a) The cross-sectional diagram of HEMT-sensor in this work. (b) The output curves of a fresh sensor exposed to air and 15 ppm H₂S at 250 °C without H₂ pre-treatment.

Fig 2. (a) The transient response curves for H₂S at 250 °C without H₂ pre-treatment. (b) The transient response curves

for H₂S at 250 °C with H₂ pre-treatment.

Fig 3. (a) Gas responses for sensors with and without H₂ pre-treatment measured at 250 °C. (b) Output curves for sensors with and without H₂ pre-treatment measured at 250 °C. (c) Transfer and g_m curves for sensors with and without H₂ pre-treatment measured at 250 °C ($V_{DS}=7$ V). (d)With H₂ pre-treatment the measurement temperature influence on I_{DS} shift ($I_{DS,shift}$, $V_{GS}=0$ V, $V_{DS}=5$ V) and threshold voltage shift ($V_{TH,shift}$).

Fig 4. AFM image for Pt film surface (a) without and (b) with H₂ pre-treatment at 250 °C.

Fig 5. The H existence status in Pt gate for sensor (a) without and (b) with H₂ pre-treatment. The H existence status in Pt gate after sensing H₂S for sensor (c) without H₂ pre-treatment and (d) with H₂ pre-treatment. **Fig 6.** The transient response curve for samples treated with H₂ at 250 °C.



